


가

가

2000 12



가 가

.....	iv
.....	vi
.....	1
.....	4
가.	4
.....	5
.....	6
.....	7
.....	9
.....	10
.....	10
.....	11
.....	12
가. hydraulic conductance(L_p)	%
.....	12
..... ,	19
.....	28
.....	36

.....	38
.....	41

Fig. 1 Schematic presentation of split chamber device	5
Fig. 2 Experimental design of Lp & AFM	8
Fig. 3 Experimental design of SEM	8
Fig. 4 Gluma: % change values of hydraulic conductance	13
Fig. 5 Seal & Protect: % change values of hydraulic conductance.....	14
Fig. 6 All-Bond 2: % change values of hydraulic conductance	15
Fig. 7 MS Coat: % change values of hydraulic conductance	16
Fig. 8-12 Gluma: SEM of dentinal surface	20,21
Fig. 13-17 Seal & Protect: SEM of dentinal surface	22,23
Fig. 18-22 All-Bond 2: SEM of dentinal surface	24,25
Fig. 23-27 MS Coat: SEM of dentinal surface	26,27
Fig. 28-32 Gluma: AFM of dentinal surface	20,21
Fig. 33-37 Seal & Protect: AFM of dentinal surface	22,23
Fig. 38-42 All-Bond 2: AFM of dentinal surface	24,25
Fig. 43-47 MS Coat: AFM of dentinal surface	26,27
Table 1 Desensitizing agents used in this study	6
Table 2 Gluma: Hydraulic conductances and % change values	13
Table 3 Seal & Protect: Hydraulic conductances and % change values	14
Table 4 All-Bond 2: Hydraulic conductances and % change values	15
Table 5 MS Coat: Hydraulic conductances and % change values	

.....	16
Table 6 Mean of Lp values and % change values	17
Table 7 Comparison of % change values before and after treatment in 4 groups	17
Table 8 Comparison of % change values among 4 groups(Kruskal-Wallis test)	18
Table 9 Comparison of % change values among 4 groups(Tukey's test)	18

가

가

가

가

1mm

, Pashely가

Gluma,

Seal & Protect, All-Bond 2, MS Coat 4

, 1 (140), 2 (280), 6 (840)

hydraulic conductance

1. hydraulic conductance가

2. Gluma, Seal & Protect, All-Bond 2

1 (140), 2 (280)

가

가 , 6 (840)

가

3. MS Coat

가

4.

, MS Coat

가

()

•

가 , 가

가 ‘

(Hydrodynamic theory)¹⁾ 가

^{2,3)}

, (hypertonic solution),


⁴⁾

가 .

Brännström^{5,6)} Anderson⁷⁾ , , , ,

가

hydraulic conductance (L_p)
 Pashely
 가
 가 2^4 가
 (Poiseuille's law),
 가 ⁸⁾
 Johnson ^{9,10,11)}
 가
 가
 Bradford ^{12,13,14)}
 가
 Rimondini ¹⁵⁾ 가
 88% 가
 , 31.3% 가
 Pashely ^{14,16,17)}
 72 86%



4

hydraulic conductance(L_p) , (Scanning Electron
 Microscopy) (Atomic Force Microscopy)

가.

60
(Isomet Buehler Co., Lake Bluff,
Illinois, U.S.A.) 1mm
120grit 30
37% 2
1
(10mm)

($\times (0.2\text{cm})^2 = 0.126\text{cm}^2$) 'O' (: 4mm,
: 10mm)
(200mmHg) 가

(Fig. 1)




Fig. 1 Schematic view of Pashely's device used to measure hydraulic conductance of dentin disc

Pressure
 cuff(Nobelpharma, Göteborg, Sweden)가 200mmHg
 가 가 가
 (1mm, 75mm),
 hydraulic conductance

가 가 가 .(Fig. 1)

4

Table 1 Desensitizing agents used in this study

	Composition	Manufacturer
Gluma Desensitizer [®]	<ul style="list-style-type: none"> · Hydroxyethylmethacrylate(HEMA) · Glutaraldehyde · Purified water · Mequinol 	Heraeus Kulzer Inc., Indiana, U.S.A.
Seal & Protect [®]	<ul style="list-style-type: none"> · PENTA · Di,Trimethacrylate · Nanofiller · Acetone · Triclosan 	Dentsply Co., Konstanz, Germany
All-Bond 2 [®]	<ul style="list-style-type: none"> · N-tolyglycine-glycidyl methacrylate(NTG-GMA) · Biphenyl dimethacrylate (BPDM) · Acetone 	Bisco Inc., Illinois, U.S.A.
MS Coat [®]	<ul style="list-style-type: none"> · Poly-styrene sulfonic acid · Poly-methyl methacrylate(PMMA) · Oxalic acid 	Sun medical Co., Shiga, Japan




Fig. 2 Experimental design of Lp & AFM




Fig. 3 Experimental design of SEM

(1) Hydraulic conductance

hydraulic conductance(L_p)

35)

$$L_p = \frac{F}{P \times (SA) \times t} \quad \text{----- ①}$$

L_p : hydraulic conductance of dentin in $\mu\ell\text{cm}^{-2}\text{min}^{-1}\text{mmHg}^{-1}$

F : filtration rate in $\mu\ell$

P : hydrostatic pressure difference across dentin in mmHg

SA : dentin surface area in cm^2

t : time in minute

P(200mmHg), SA($\times (0.2\text{cm})^2 = 0.126\text{cm}^2$), t(10minutes) 3

L_p F

$$L_p = \frac{F}{P \times (SA) \times t} \quad \text{----- ②}$$

F mm

$$F = \frac{1}{4} \times (0.5)^2 \times \frac{1}{4} \times 10^3 \quad \text{----- ③}$$

② ③ L_p

$$L_p = \frac{F}{P \times (SA) \times t} \quad \text{----- ④}$$

hydraulic conductance(L_p) ()가

①

$$L_p = \frac{F}{P \times (SA) \times t} = \frac{\frac{1}{4} \times (0.5)^2 \times \frac{1}{4} \times 10^3}{200 \times \frac{1}{4} \times (0.2)^2 \times 10} = \frac{25}{8} \quad \text{----- ⑤}$$

(2) %

L_p %

$$\% = \frac{L_p - L_p(L_p0)}{L_p(L_p0)} \times 100 \quad \text{----- } \textcircled{6}$$

%change1: $L_p(L_p1)$

$L_p(L_p0)$ %

%change2: 1 (140) $L_p(L_p2)$ $L_p(L_p0)$

%

%change3: 2 (280) $L_p(L_p3)$ $L_p(L_p0)$

%

%change4: 6 (840) $L_p(L_p4)$ $L_p(L_p0)$

%

(Scanning Electron Microscopy)

SEM

stud gold sputter-coating 3,000

(Fig. 3)

(Atomic Force Microscope)

3

.(Fig. 2)

•

L_p 가

, L_p

Kruskal-Wallis test

multiple comparison test

,

Wilcoxon signed rank test

, Tukey's

.

•

가. ,

hydraulic conductance (L_p) %

60 L_p , % Table

2 5 , Fig. 4 7 L_p %

Table 6 .

Gluma % -88.46

가 1 (140), 2 (280)

% -76.32, -62.05 가 가

가 6 (840)

% -92.96 Gluma 가

Seal & Protect All-Bond 2 Gluma

가

1 (140), 2 (280) 가 가

6 (840)

MS Coat % -99.61

가 1 (140), 2 (280), 6

(840) % -72.15, -71.83, -74.73

가 가 .

Table 2 Gluma: Hydraulic conductances and % change values

	Lp 0	Lp 1 %	1	Lp 2 %	2	Lp 3 %	3	Lp 4 %	4
1	1.56	0.00	-100.0	0.78	-50.0	0.78	-50.0	0.78	-50.0
2	29.69	2.34	-92.1	0.00	-100.0	0.00	-100.0	0.00	-100.0
3	3.13	0.00	-100.0	0.00	-100.0	2.34	-25.0	0.00	-100.0
4	63.28	0.00	-100.0	0.00	-100.0	2.34	-96.3	0.78	-98.8
5	40.63	0.00	-100.0	0.00	-100.0	2.34	-94.2	0.00	-100.0
6	32.81	3.13	-90.5	3.13	-90.5	6.25	-81.0	0.00	-100.0
7	75.78	5.47	-92.8	8.59	-88.7	21.09	-72.2	1.56	-97.9
8	149.22	0.00	-100.0	0.78	-99.5	1.56	-99.0	0.00	-100.0
9	53.91	0.78	-98.6	0.78	-98.6	1.56	-97.1	1.56	-97.1
10	3.13	0.00	-100.0	0.00	-100.0	2.34	-25.0	0.00	-100.0
11	57.03	14.84	-74.0	27.34	-52.1	42.19	-26.0	4.69	-91.8
12	5.47	0.78	-85.7	0.00	-100.0	0.78	-85.7	0.78	-85.7
13	22.66	0.00	-100.0	7.81	-65.5	4.69	-79.3	1.56	-93.1
14	2.34	1.56	-33.3	2.34	0.0	2.34	0.0	0.00	-100.0
15	7.81	3.13	-60.0	7.81	0.0	7.81	0.0	1.56	-80.0




Fig. 4 Gluma: % change values of hydraulic conductance

Table 3 Seal & Protect: Hydraulic conductances and % change values

	Lp 0	Lp 1 %	1	Lp 2 %	2	Lp 3 %	3	Lp 4 %	4
1	24.22	0.00	-100.0	3.13	-87.1	1.56	-93.5	1.56	-93.5
2	14.84	0.00	-100.0	0.78	-94.7	0.00	-100.0	0.00	-100.0
3	8.59	0.00	-100.0	0.78	-90.9	1.56	-81.8	0.00	-100.0
4	7.03	1.56	-77.8	1.56	-77.8	1.56	-77.8	1.56	-77.8
5	39.84	2.34	-94.1	3.13	-92.2	3.91	-90.2	2.34	-94.1
6	12.50	0.00	-100.0	0.78	-93.8	1.56	-87.5	0.00	-100.0
7	23.44	0.00	-100.0	6.25	-73.3	0.78	-96.7	0.78	-96.7
8	27.34	0.00	-100.0	0.00	-100.0	3.13	-88.6	0.00	-100.0
9	4.69	0.00	-100.0	0.00	-100.0	2.34	-50.0	1.56	-66.7
10	54.69	0.00	-100.0	0.78	-98.6	8.59	-84.3	7.81	-85.7
11	9.38	0.00	-100.0	0.78	-91.7	1.56	-83.3	0.00	-100.0
12	10.94	0.00	-100.0	0.78	-92.9	1.56	-85.7	0.00	-100.0
13	13.28	0.00	-100.0	0.78	-94.1	2.34	-82.4	0.00	-100.0
14	12.50	0.00	-100.0	0.78	-93.8	1.56	-87.5	0.00	-100.0
15	32.03	0.78	-97.6	0.78	-97.6	0.78	-97.6	0.00	-100.0




Fig. 5 Seal & Protect: % change values of hydraulic conductance

Table 4 All-Bond 2: Hydraulic conductances and % change values

	Lp 0	Lp 1 %	1	Lp 2 %	2	Lp 3 %	3	Lp 4 %	4
1	3.13	0.00	-100.0	0.00	-100.0	0.00	-100.0	0.78	-75.0
2	47.66	4.69	-90.2	0.00	-100.0	19.53	-59.0	17.97	-62.3
3	31.25	0.00	-100.0	0.00	-100.0	1.56	-95.0	1.56	-95.0
4	8.59	0.78	-90.9	0.78	-90.9	3.91	-54.5	2.34	-72.7
5	20.31	0.78	-96.2	1.56	-92.3	3.91	-80.8	2.34	-88.5
6	22.66	0.00	-100.0	3.13	-86.2	4.69	-79.3	3.13	-86.2
7	9.38	0.00	-100.0	0.78	-91.7	1.56	-83.3	0.00	-100.0
8	7.81	0.78	-90.0	1.56	-80.0	1.56	-80.0	0.78	-90.0
9	4.69	0.00	-100.0	1.56	-66.7	1.56	-66.7	0.00	-100.0
10	9.38	0.00	-100.0	0.78	-91.7	0.78	-91.7	0.78	-91.7
11	3.13	0.00	-100.0	2.34	-25.0	2.34	-25.0	0.00	-100.0
12	11.72	0.00	-100.0	0.78	-93.3	0.78	-93.3	0.00	-100.0
13	14.06	0.00	-100.0	1.56	-88.9	3.91	-72.2	1.56	-88.9
14	19.53	0.78	-96.0	0.78	-96.0	1.56	-92.0	0.00	-100.0
15	281.25	21.09	-92.5	4.69	-98.3	5.47	-98.1	3.13	-98.9




Fig. 6 All-Bond 2: % change values of hydraulic conductance

Table 5 MS Coat: Hydraulic conductances and % change values

	Lp 0	Lp 1 %	1	Lp 2 %	2	Lp 3 %	3	Lp 4 %	4
1	21.09	0.00	-100.0	4.69	-77.8	1.56	-92.6	3.13	-85.2
2	215.63	0.78	-99.6	8.59	-96.0	2.34	-98.9	3.91	-98.2
3	18.75	0.00	-100.0	4.69	-75.0	5.47	-70.8	4.69	-75.0
4	32.03	0.00	-100.0	7.81	-75.6	8.59	-73.2	9.38	-70.7
5	109.38	0.00	-100.0	5.47	-95.0	6.25	-94.3	25.78	-76.4
6	47.66	0.00	-100.0	3.13	-93.4	1.56	-96.7	3.13	-93.4
7	16.41	0.00	-100.0	3.91	-76.2	5.47	-66.7	3.13	-81.0
8	6.25	0.00	-100.0	4.69	-25.0	0.78	-87.5	0.78	-87.5
9	3.13	0.00	-100.0	0.78	-75.0	0.78	-75.0	0.78	-75.0
10	17.19	0.00	-100.0	3.13	-81.8	3.13	-81.8	2.34	-86.4
11	11.72	0.00	-100.0	2.34	-80.0	0.78	-93.3	5.47	-53.3
12	14.06	0.78	-94.4	1.56	-88.9	4.69	-66.7	8.59	-38.9
13	12.50	0.00	-100.0	4.69	-62.5	12.50	0.0	0.00	-100.0
14	6.25	0.00	-100.0	6.25	0.0	6.25	0.0	0.00	-100.0
15	3.91	0.00	-100.0	0.78	-80.0	0.78	-80.0	3.91	0.0




Fig. 7 MS Coat: % change values of hydraulic conductance

Table 6 Mean of Lp values and %change values

Agent	Lp 0	Lp 1	% change1	Lp 2	% change2	Lp 3	% change3	Lp 4	% change4
Gluma	36.56	2.14	-88.46	3.96	-76.32	6.56	-62.05	0.89	-92.96
Seal&Protect	19.69	0.31	-97.96	1.41	-91.89	2.19	-85.79	1.04	-94.30
All-Bond 2	32.97	1.93	-97.05	1.35	-86.73	3.54	-78.06	2.29	-89.94
MS Coat	35.73	0.10	-99.61	4.17	-72.15	4.06	-71.83	5.00	-74.73

Wilcoxon signed rank test, Gluma, Seal & Protect, All-Bond 2, MS Coat. (p < 0.05, Table 7)

Table 7 Comparison of % change values before and after treatment in 4 groups (Wilcoxon signed rank test)

	Gluma	Seal&Protect	All-Bond 2	MS Coat
% change2- % change1	0.0742	0.0010*	0.0234*	0.0001*
% change3- % change2	0.0137*	0.0654	0.0039*	0.9883
% change4- % change3	0.0010*	0.0010*	0.0129*	0.7708

*: p < 0.05, statistically significant

Kruskal-Wallis test, Tukey's multiple comparison test. (Table 8 9)

Table 8 Comparison of % change values among 4 groups
(Kruskal-Wallis test)

	% change1	% change2	% change3	% change4
P-value	0.0318*	0.0409*	0.4074	0.0089*

*: p < 0.05, statistically significant

Table 9 Comparison of % change values among 4 groups
(Tukey's multiple comparison test)

	Gluma	Seal & Protect	All-Bond 2	MS Coat
% change1	B	—	—	A
% change2	—	A	—	B
% change4	A	A	—	B

Groups with different letter are different each other statistically.
Comparison between same group is meaningless.

1 MS Coat Gluma가
, MS Coat가 Gluma 1
. 2
1 Seal & Protect MS
Coat가 , MS Coat가 Seal & Protect
. 6 2
MS Coat Seal & Protect,
MS Coat Gluma가 , MS Coat가 Seal &
Protect, Gluma .

Fig. 8 12, 28 32 Gluma . Fig.
 9 Gluma , Fig. 10
 Gluma가
 , Fig. 11 2
 , Fig. 12 6
 . Fig. 28 32
 Fig. 13 17, 33 37 Seal & Protect
 . Fig. 14 Seal & Protect
 . Fig. 15 17 Seal & Protect가
 가 . Fig. 16 17 Seal & Protect가
 . Fig. 33 37
 Fig. 18 22, 38 42 All-Bond 2
 . Fig. 19 All-Bond 2
 . Fig. 20 22 가
 . Fig. 38 42
 Fig. 23 27, 43 47 MS Coat . Fig.
 24 MS Coat .
 Fig. 25 27 MS Coat가 가
 . Fig. 23 27
 . Fig. 43 47




Fig. 8 Gluma: SEM of dental surface: before agent treatment




Fig. 28 Gluma: AFM of dental surface: before agent treatment




Fig. 9 Gluma: SEM of dental surface: after agent treatment




Fig. 29 Gluma: AFM of dental surface: after agent treatment




Fig. 10 Gluma: SEM of dental surface: after 1-week tooth brushing




Fig. 30 Gluma: AFM of dental surface: after 1-week tooth brushing




Fig. 11 Gluma: SEM of dental surface: after 2-week toothbrushing




Fig. 31 Gluma: AFM of dental surface: after 2-week tooth brushing




Fig. 12 Gluma: SEM of dental surface: after 6-week tooth brushing




Fig. 32 Gluma: AFM of dental surface: after 6-week tooth brushing




Fig. 13 S & P: SEM of dental surface: before agent treatment




Fig. 33 S & P: AFM of dental surface: before agent treatment




Fig. 14 S & P: SEM of dental surface: after agent treatment




Fig. 34 S & P: AFM of dental surface: after agent treatment




Fig. 15 S & P: SEM of dental surface: after 1-week tooth brushing




Fig. 35 S & P: AFM of dental surface: after 1-week tooth brushing




Fig. 16 S & P: SEM of dental surface: after 2-week tooth brushing




Fig. 36 S & P: AFM of dental surface: after 2-week tooth brushing




Fig. 17 S & P: SEM of dental surface: after 6-week tooth brushing




Fig. 37 S & P: AFM of dental surface: after 6-week tooth brushing




Fig. 18 All-Bond: SEM of dentinal surface: before agent treatment




Fig. 38 All-Bond: AFM of dentinal surface: before agent treatment




Fig. 19 All-Bond: SEM of dentinal surface: after agent treatment




Fig. 39 All-Bond: AFM of dentinal surface: after agent treatment




Fig. 20 All-Bond: SEM of dentinal surface: after 1-week tooth brushing




Fig. 40 All-Bond: AFM of dentinal surface: after 1-week brushing




Fig. 21 All-Bond: SEM of dentinal surface: after 2-week tooth brushing




Fig. 41 All-Bond: AFM of dentinal surface: after 2-week tooth brushing




Fig. 22 All-Bond: SEM of dentinal surface: after 6-week tooth brushing




Fig. 42 All-Bond: AFM of dentinal surface: after 6-week tooth brushing




Fig. 23 MS Coat: SEM of dental surface: before agent treatment




Fig. 43 MS Coat: AFM of dental surface: before agent treatment




Fig. 24 MS Coat: SEM of dental surface: after agent treatment




Fig. 44 MS Coat: AFM of dental surface: after agent treatment




Fig. 25 MS Coat: SEM of dental surface: after 1-week tooth brushing




Fig. 45 MS Coat: AFM of dental surface: after 1-week tooth brushing




Fig. 26 MS Coat: SEM of dentinal surface: after 2-week tooth brushing




Fig. 46 MS Coat: AFM of dentinal surface: after 2-week tooth brushing




Fig. 27 MS Coat: SEM of dentinal surface: after 6-week tooth brushing




Fig. 47 MS Coat: AFM of dentinal surface: after 6-week tooth brushing

•

2,3)

8,18)

19)

18)

가

2-7 μ m

20)

8,18)

80% 가
가

()

, -
(predentin)

가 가 ,
가 가 . ,
가

가

(intratubular

dentin)

(apatite crystal)

type I

(intertubular

dentin)

2.5 μ m,

0.8 μ m ²¹⁾

1 5 μ m
가⁴⁾

, Pashely

가

22,23,24)

Brännström

²⁵⁾,

가

가

26,27)

Garcia

²⁷⁾, Srisawaski

가

²⁸⁾

가

7 1

²⁹⁾

가

Rimondini, Absy

가

15,30)

Oxalate Glutaraldehyde

가

가

가

가

가

가

가

가

Pashely가

hydraulic conductance(L_p)

'O'

4

15

가

가

가

1mm

(

: $1.03 \pm 0.097\text{mm}$)

가

가

¹⁴⁾.

가

가

²²⁾.

hydraulic conductance(L_p)가

가

가 가 L_p % 가 가 ³¹⁾
Hydraulic conductance 가 가 . Pashely

가 가 가 가 가 가
가 가 가 가 가 가
Pashely ³²⁾ , , ,

가 가 가 가 가 가 가 가 가 가
25 35 10 가 가 2 가 가
가 가 가 가 가 가 가 가 가 가
^{33,34)} 가 가 가 가 가 가 가 가 가 가

가 가 가 가 가 가 가 가 가 가
³³⁾ 가 가 가 가 가 가 가 가 가 가
Brännström 가 가 가 가 가 가 가 가 가 가
120grit 가 가 가 가 가 가 가 가 가 가
30 가 가 가 가 가 가 가 가 가 가
Dippel 가 가 가 가 가 가 가 가 가 가

¹⁴⁾

가 ,

Gluma desensitizer[®], Seal & Protect[®], All-Bond 2[®], MS Coat[®] 4

가 .

Gluma desensitizer 5% glutaraldehyde 35% hydroxyethylmethacrylate(HEMA) . Glutaraldehyde

HEMA , glutaraldehyde

glutaraldehyde가

Bergenholtz Gluma

³⁵⁾ Gluma

12 가 Schüpbach

Gluma 가 ³⁶⁾

Seal & Protect PENTA di-,trimethacrylate resin, nanofiller, , acetone, triclosan .

All-Bond 2 resin-based adhesive A,B primer . primer

N-tolyglycine-glycidyl methacrylate(NTG-GMA) biphenyl dimethacrylate polymer matrix . All-Bond 2 , Ianzano

8 42 All-Bond 2

6 가 ³⁷⁾ Tay in vivo All-Bond 2 , acetone

primer (hybrid layer)

· , (1) (hybrid layer)

, (2) globule hollow

resin sheath inner zone

³⁸⁾ .

MS Coat Polymer-reinforced precipitate poly-styrene

sulfonic acid, polymethyl methacrylate, oxalic acid . MS Coat
 , reactive polymer
 가 . Camps
 Protect[®], Gluma[®], MS Coat[®]가
 , 60 85% MS Coat
 가 가 (85%) ³⁵⁾. Zhang MS
 Coat가 , MS Coat
 가 ,
 가

Poly-styrene sulfonic acid ³⁹⁾.
 37%
 Seal & Protect

()⁴ Poiseuille's law
 ()

가 (,) ,
 Oral-B[®] (nylon-tufted, Oral-B Inc., Belmont, CA, U.S.A.)
 200mmHg (26.7kPa) 가 ,
 14.1cmH₂O (1.38kPa) ,

³⁵⁾

가

. Camps ³⁵⁾

가

(serum)

가

가

4가

. (MS Coat: 99.61%, Seal & Protect: 97.96%, All-Bond 2: 97.05%, Gluma: 88.46%) , MS Coat 3
6 (840) 가

. Jain , ,

⁴⁰⁾ MS

Coat

Zhang

가

3

³⁹⁾ Suggs

30

MS Coat

가

⁴¹⁾

MS Coat

가

poly-styrene sulfonic acid

가

, MS Coat

가

가

가

. Zhang³⁹⁾

가

가

4가

•

가

가

1mm

, Pashely가

Gluma desensitizer[®], Seal & Protect[®], All-Bond 2[®], MS Coat[®] 4

, 1 , 2 , 6

hydraulic conductance

,

.

1. hydraulic conductance가

. (MS Coat: 99.61%, Seal & Protect: 97.96%, All-Bond 2: 97.05%,
Gluma: 88.46%)

2. Gluma, Seal & Protect, All-Bond 2

1 (140), 2 (280)

가

가

, 6 (840)

가

.

3. MS Coat

가

.

4.

.

, MS Coat

Gluma, Seal & Protect, All-Bond 2

3

1. Brännström M., Linden L., Johnson G.: Movement of dentinal and pulpal fluid caused by clinical procedures. *J Dent Res* 47:679-682, 1968.
2. Anderson D.J., Matthews B., Shelton L.E.: Variations in the sensitivity to osmotic stimulation of human dentin. *Arch Oral Biol* 12:43, 1967.
3. Brännström M., Johnson G., Nordenvall K-J: Transmission and control of dentinal pain : Resin impregnation for the desensitization of dentin. *J Am Dent Assoc* 99:612, 1979.
4. Rauschenberge C.R.: Dentin permeability. The clinical ramification. *DCNA* 36:527-542, 1992.
5. Brännström M., Astrom A.: A study on the mechanism of pain elicited from the dentin. *J Dent Res* 43:619-625, 1964.
6. Brännström M., Linden L., Johnson G.: Movement of dentinal and pulpal fluid caused by clinical procedures. *J Dent Res* 47:679-682, 1968.
7. Anderson D.J., Matthews B., Gorretta G.: Fluid flow through human dentin. *Arch Oral Biol* 12:209-216, 1969.
8. Pashely D.H., Carvalho R.M.: Dentin permeability and dentin adhesion. *J Dent* 25:355-372, 1997.
9. Brännström M., Johnson G., Linden L.: Fluid flow and pain response in the dentin produced by hydrostatic pressure. *Odont Revy* 20:16-30, 1969.
10. Johnson G., Brännström M.: The sensitivity of dentin : Changes in relation to conditions at exposed tubule apertures. *Acta Odont Scandl* 32:29-38, 1974.
11. Reeder Jr O.W., Walton R.E., Livingstone M.J., Pashely D.H.: Dentin permeability : Determinants of hydraulic conductance. *J Dent Res* 57(2):187-193, 1978.
12. Brännström M., Johnson C.: Effect of various conditions and cleaning agent on prepared dentin surfaces : A scanning electron microscopic investigation. *J Prosthet Dent* 31:422, 1974.
13. Bradford E.A.: The dentine a barrier to caries. *Br Dent J* 109:387, 1960.
14. Dippel H.W., Borggreven J.M.P.M., Hoppenbrouwers P.M.M.: Morphology and permeability of the dentinal smear layer. *J Prosthet Dent* 52:657-662, 1984.
15. Rimondini L., Baroni C., Carrass A.: Ultrastructure of hypersensitive

- and non-hypersensitive dentin : A study on replica models. *J Clin Periodontol* 22:899-902, 1995.
16. Pashely D.H., Livingstone M.J., Greenhill J.D.: Regional resistances to fluid flow in human dentin in vitro. *Arch Oral Biol* 23:807, 1978.
 17. Pashely D.H., Livingstone M.J., Outhwaite W.: Dentin permeability changes produced by iontophoresis. *J Dent Res* 57:77, 1978.
 18. Pashely D.H., Ciucchi G., Sano H., Homer J.A.: Permeability of dentin to adhesive agents. *Quintessence International* 24:618-631, 1993.
 19. Brännström M.L., Linden A., Storom A.: The hydrodynamics of dentin and pulp fluid : Its significance in relation to dental pain. *Caries Res* 1:310-317, 1967.
 20. Nakabayashi N., Kojima K., Masuhara E.: Promotion of adhesion by the infiltration of monomers into tooth substrates. *J Biomedical Materials Research* 16:265-273, 1982.
 21. Marshall G.W., Marshall S.J., Kinney J.H., Balooch M.: The dentin substrate : structure and properties related to bonding. *J Dent* 25:441-458, 1997.
 22. Pashely D.H., Michelich V., Kehl T.: Dentin permeability : Effects of smear layer removal. *J Prosthet Dent* 46:531-536, 1981.
 23. Pashely D.H.: Smear layer : Physiologic considerations. *Oper Dent* 9:13-29, 1984.
 24. Wieman A., Drake D.: Effect of smear layer on in vitro root canal bacterial colonization. *J Endodontics* 17:189, 1991.
 25. Strassler H.E., Nathanson D.: The new generation dentin bonding agents. *Alpha Omega* 81:28, 1988.
 26. Brännström M.: Smear layer: Pathological and treatment considerations. *Oper Dent* suppl 3:35-42, 1984.
 27. Garcia-Godoy F.: Dentin surface treatment and shear bond strength of a light-cured glass ionomer. *Am J Dent* 5:283-285, 1992.
 28. Srisawaski S., Boyer D.B., Reinhardt J.W.: The effect of removal of the smear layer on microleakage of class V restorations in vitro. *Dent Mater* 4:384-389, 1988.
 29. Graf H., Galasse R.: Morbidity, prevalence and intra-oral distribution of hypersensitivity teeth. *J Dent Res* 56:162, 1977.
 30. Absy E.G., Addy M., Adams D.: A study of the patency of dentinal tubules in sensitive and non-sensitive cervical dentin. *J Clin Periodontol* 14:280-284, 1987.

31. Greenhill J.D., Pashely D.H.: The effect of desensitizing agent on the hydraulic conductance of human dentin in vitro. *J Dent Res* 60:686-698, 1981.
32. Pashely D.H., Andringa H.J., Derkson G.D., Derkson M.E., Kalathoor S.R.: Resional variability in the permeability of human dentin. *Arch Oral Biol* 32:519-523, 1987.
33. Reeder O.W., Livingstone M.J., Pashely D.H.: Effects of changes in surface area, thickness, temperature, and post extraction time on human dentin permeability. *Arch Oral Biol* 21:599-603, 1976.
34. Goodis H.E., Marshall Jr G.W., White J.M.: The effects of storage after extraction of the teeth on human dentin permeability in vitro. *Arch Oral Biol* 36:561-566, 1991.
35. Camps J., Pizant S., Dejous J., Franquin J.C.: Effect of desensitizing agents on human permeability. *Am J Dent* 11:286-290, 1998.
36. Schüpbach P., Lutz F., Finger W.W.: Closing of dentinal tubules by Gluma desensitizer. *Eur J Oral Sci* 105:414-421, 1997.
37. Ianzano J.A., Gwinnett A.J., Westbay G.: Polymeric sealing of dentinal tubules to control sensitivity.: *Periodontol Clin Invest* 15:13-16, 1993.
38. Tay F.R., Gwinnett A.J., Pang K.M., Wei S.H.Y.: Structural evidence of a sealed tissue interface with a total etch wet bonding technique, in vitro. *J Dent Res* 73:629-636, 1994.
39. Zhang Y., Agee K., Pashley D.H.: The effects of Pain-Free desensitizer on dentin permeability and tubule occlusion over time, in vitro. *J Clin Periodontol* 25:884-891, 1998.
40. Jain P., Vargas M.A., Denehy G., Boyer D.B.: *Am J Dent* 10:21-27, 1997.
41. Suggs A.K., Cox C.F., Cox L.K., Suzuki S., Suzuki S.H.: Colloidal MSE for differential diagnosis and treatment of dentin hypersensitivity. Presented at Chiba Japan July 3rd through 6th 1995.
42. , , : 가 .
: vol.38, No.4, 2000

ABSTRACT

The Effects of Desensitizing Agents and Tooth Brushing on Dentin Permeability, in vitro

JONG-WOOK LEE, D.D.S.

Department of Dental Science, Graduate School, Yonsei University

(Directed by Professor **KEUN-WOO LEE, D.D.S., M.S.D., Ph.D.**)

Desensitizing agents are commonly used in tooth sensitivity but their effects are often for a short duration. One of the reasons is believed to be wear of desensitizing agent although it has been rarely studied.

To study the effect of dentin permeability on a tooth with wear from tooth brushing after application of desensitizing agent, extracted teeth free from caries were chosen. Coronal dentin discs with thickness of 1mm were prepared. Using the split chamber device developed by Pashely, hydraulic conductance, scanning electron microscope images(SEM) and atomic force microscope images(AFM) were compared and contrasted before and immediately after the application of desensitizing agent and after equivalent tooth brushing of 1 week, 2 weeks, and 6 weeks. Four commercially available desensitizing agents were used in this study; they were Gluma, Seal & Protect, All-Bond 2 and MS Coat. The results of this study are as follows.

1. On all specimens, the hydraulic conductance decreased after the application of tooth desensitizing agent.
2. Except the specimens treated with MS Coat, the remaining specimens had an increase in dentin permeability after tooth brushing for 1 and 2 weeks but a decrease after 6 weeks.
3. The specimens treated with MS Coat had statistically significant increase in the dentin permeability regardless with the duration of tooth brushing.

4. On examination of SEM and AFM, the dentinal tubule diameter had decreased after treatment of desensitizing agents. The specimens other than those treated with MS Coat, smear layers were noted after tooth brushing. It is not always consistent but the hydraulic conductance correlated with the images from SEM and AFM.

Reflecting the above results, the effect of desensitizing agent in tooth sensitivity from obstructing dentinal tubules is temporary. The dentinal sensitivity should therefore be treated initially with a desensitizing agent but followed by tooth brushing for a prolonged management.

Key words : dentin permeability, desensitizing agent, tooth sensitivity, smear layer